

Typical Mechanical & Electrical Properties of GRP Rods & Tubes (Upto 31.8mm)

Unidirectional E Glass rovings

Flexural Strength	650MN/m ²
Flexural Modulus	30GN/m ²
Tensile Strength	500MN/m ²
Tensile Modulus	27GN/m ²
Density	1.8gm/cc
Water Absorption	0.5% – 2%
Compressive Strength	190MN/m ²
Coefficient of Thermal Expansion	7.2 x 10 ⁻⁶ /K
Barcol Hardness	40-70
Heat Distortion Temp	125-145°C
Electrical Surface Resistivity	10 ¹² OHMS (Between 10 ¹⁰ - 10 ¹⁵)
Volume Resistivity	10 ¹⁵ OHMS
Insulation Resistance	M Ohm 1000
Dielectric Strength @ 90 ⁰	Kv/mm 25
Dielectric Strength @ 90 ⁰	KV 75
Permittivity @ 50 Hz	5
Dissipation Factor	0.02
Comparative Tracking	V 600
Arc Resistance	s 300

Accuracy

Small Rod Tolerance up to 6mm

Polyester +0.05/-0.07

Vinyl Ester +0.05/-0.15

Calorific content of 811 resin	28mj/kg
30% glass	19 mj/kg
55%-60% glass	10-15mj/kg





RBJ Reinforced Plastics Ltd
Specialists in Pultruded GRP Sections and Profiles

Unit 1 Woodcock Hill Industrial Estate
Harefield Road Rickmansworth Herts WD3 1PQ

T: +44 (0) 1923 778853
F: +44 (0) 1923 896080
E: info@rbjplastics.com
W: www.rbjplastics.com

Available Resin Types

Polyester Orthothalic
 Isothalic Resins

Vinyl Ester

Acrylic

